

## VLM 3301

<b>FACING COMPOSITION</b>	<b>DESCRIPTION</b>
Film	Ester Polyurethane Film

### Tentative Specification

<b>PHYSICAL PROPERTIES</b>	<b>TEST METHOD</b>	<b>VALUES (ENGLISH)</b>
Durometer	ASTM D2240	90 Shore A
Color	Black / Clear / Colors	
Caliper / Thickness	Micrometer	0.0015 inch
Elomgation @ Break	ASTM D412	515% +
Tensile Strength	ASTM D412	5400 PSI ~
100 % Modulus	ASTM D412	1500PSI~
300% Modulus	ASTM D 412	2950% ~
Melt Range		375-425 Deg F (190-220 Deg C)

Physical Properties based upon Minimum statistical averages